



INFORMATION BULLETIN

Burned Magnesite Brick– Atlas 95TI Tar Impregnated

Typical Chemical Analysis

Approximate % - calcined basis

MgO	> 95.10%
CaO	< 1.50%
Silica	< 2.0%
Fe ₂ O ₃	< 0.8%
Al ₂ O ₃	< 0.8%

Typical Physical Properties

Bulk Density g/cm ³	3.07
Cold Crushing Strength Mpa	55.0
Apparent Porosity %	< 18 (before impregnation)
Modulus of rupture %	< 7 (after impregnation)
@22°C	15.86
@1482°C	2.76
Refractoriness under load, °C	1620

(REV 08/05)