



# Bastion

## Magnesia Alumina Carbon Brick

Sometimes referred to as:  
Magnesia Alumina Graphite Brick

---

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

Al <sub>2</sub> O <sub>3</sub>	.....	10%	by weight (approx.)
MgO	.....	78%	
C	.....	7%	

### Typical As Received Properties:

Bulk Density, original	3.00 g/cm <sup>3</sup>
Cold Crushing Strength	> 8000 psi
Apparent Porosity	< 5%

04/2002