



Durachrome® 60C – Mag-Chrome Brick

Durachrome® 60C: Direct-bonded, high density mag-chrome brick.

USES INCLUDE: Ladle slag lines
Degasser sidewalls
AODs
EAF sidewalls
Copper smelters
Nickel smelters
Lead smelters

Typical Chemical Analysis

Approximate % - calcined basis

Mgo	69%
Cr ₂ O ₃	18%
SiO ₂	1.1%
Al ₂ O ₃	4%
Fe ₂ O ₃	6%
CaO	1.3%

Typical Physical Properties

Apparent Porosity %	16
Bulk Density g/cm ³	3.16

Note: The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

(REV 6/05)

**“Mailing Address” P.O. Box 278, Westmount Station, Montreal, Quebec, H3Z 2T2
Tél.: (514) 931-5711 • 1-800-609-5711 • Fax.: (514) 931-8378**