



FLOSAN® 2007

Flosan® 2007: E.B.T Furnace taphole sand with high refractoriness to provide for outstanding free open rates.

Typical Chemical Analysis

		FLOSAN® 2007
MgO	%	35 – 45
SiO ₂	%	45 – 55
Fe ₂ O ₃	%	5 – 10
CaO	%	1 – 2
Al ₂ O ₃	%	1 – 2
C	%	Yes

Packaging and Storage:

Shipped in either 1400 KG super sacks (approx. 3,086 lbs), 1000 lb drums, or 50 lb bags. Other packaging options may also be available.

Store pallets in a dry and protected area.

(REV. 050314)

1 (800) 609-5711

Tel.: (514) 931-5711

www.fedmet.com

Fax: (514) 931-8378