



## FLOSAN® GDS

---

Flosan® GDS is a mixture of carefully selected and processed refractory materials with a high sintering point. The product is used as nozzle fill in sliding gate ladle systems, and can also be used in E.B.T. furnace taphole.

### Typical Chemical Analysis

		FLOSAN® GDS
Cr <sub>2</sub> O <sub>3</sub>	%	30 – 35
MgO	%	5 – 10
Al <sub>2</sub> O <sub>3</sub>	%	10 – 15
SiO <sub>2</sub>	%	25 – 30
C	%	Yes
Fe <sub>2</sub> O <sub>3</sub>	%	15 – 20

### Packaging and Storage:

Shipped in either 1400 KG super sacks (approx. 3,086 lbs), 1000 lb drums, or 50 lb bags. Other packaging options may also be available.

Store pallets in a dry and protected area.

(REV. 050314)

---

**1 (800) 609-5711**

Tel.: (514) 931-5711

www.fedmet.com

Fax: (514) 931-8378