



## Alumina-Mag-Carbon – ORACLE® IP

---

### Typical Chemical Analysis

Al <sub>2</sub> O <sub>3</sub>	87% by weight (approx)
MgO	11%
SiO <sub>2</sub>	2%
C	5%

### Typical as Received Properties

Bulk Density, original	3.22 g/cm <sup>3</sup>
Cold Crushing Strength	95 MPa
Apparent Porosity	4%

REV (09/05)