



Alumina-Mag-Carbon – ORACLE (Standard)

Typical Chemical Analysis

Al ₂ O ₃	80%	by weight (approx)
MgO	11 %	
SiO ₂	4%	
C	5%	

Typical as Received Properties

Bulk Density, original	2.94 g/cm ³
Cold Crushing Strength	95 MPa
Apparent Porosity	5%

REV (09/05)