



## Atlas 95: Burned Magnesite Brick

---

**DESCRIPTION:** Burned and ceramically bonded magnesite brick. Available with or without tar impregnation. Burned brick has a higher porosity than chemically bonded brick, so in certain applications, tar could help reduce slag penetration.

**USES INCLUDE:** EAF sub-hearth.  
BOF ladle safety lining.

### CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % - calcined basis)

MgO	95.0%
Silica	1.6%
CaO	1.4%
Fe <sub>2</sub> O <sub>3</sub>	1.1%
Al <sub>2</sub> O <sub>3</sub>	0.7%

### TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity (%)	< 18 (before impregnation)
Bulk Density, original g/cm <sup>3</sup> (pcf)	2.94 (183)
Cold Crushing Strength MPa (psi)	100 (14,500)
Modulus of rupture MPa (psi):	
@ 22° C (° F)	15 (2175)
@ 1482° C (° F)	3 (435)
Refractoriness under load ° C (° F)	1620 (2948)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 21.03

---