



Fedhearth 75

DESCRIPTION: An electric furnace ramming mix, dry, manufactured from dead burned magnesia, with high lime content, reduced iron content, and high density.

USES INCLUDE: New bottoms of electric arc furnaces.
Hot or cold patches.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate % by weight)

MgO	69.0%
CaO	26.6%
Fe ₂ O ₃	1.9%
SiO ₂	1.02%
Al ₂ O ₃	0.55%

TYPICAL AS RECEIVED PROPERTIES:

Shipped in (kg bags):	500, 1000, 2000
Storage (pallets):	dry and protected area

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
