



Fedvibe M

DESCRIPTION: Basic dry ramming material, which has good filling and ramming properties. It has good low, intermediate, and high-temperature strength. It has no offensive odor.

USES INCLUDE: Filler.
Patching.
Leveling.
Dry ramming.

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

(Approximate %)

MgO	89.5%
CaO	3.2%
SiO ₂	6.3%
Fe ₂ O ₃	0.8%
Al ₂ O ₃	0.2%

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, pcf (g/cm ³):	169 (2.7)
Maximum Grain Size (mesh):	5
Maximum Service Temp (° F):	3400

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally and as a function of size and shape. This form is not intended to be used for purposes of specification; it is informational only.

Version 20.11
