



Epic® 70PT

DESCRIPTION: High-alumina shapes that are extruded or dry-pressed depending on shape

USES INCLUDE: Hollow ware for steel pouring

CHEMICAL ANALYSIS:

Alumina	Al ₂ O ₃	70%
Silica	SiO ₂	24.0%
Ferric Oxide	Fe ₂ O ₃	2.4%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity, %	28
Bulk Density g/cm ³	2.25
Cold Crushing Strength, Mpa	25
Refractoriness (°C)	1790

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 13.5
