

**FLOSAN<sup>®</sup>**

---

**DESCRIPTION:** Flosan<sup>®</sup> is a mixture of carefully selected and processed refractory materials with a high sintering point. The product is used as nozzle fill in sliding gates ladle system and also in E.B.T. furnace taphole.

**CHEMICAL ANALYSIS:**

		FLOSAN <sup>®</sup>
Cr <sub>2</sub> O <sub>3</sub>	%	34 – 38
MgO	%	7 – 10
Al <sub>2</sub> O <sub>3</sub>	%	10 – 14
SiO <sub>2</sub>	%	22 – 26
C	%	Yes
Fe <sub>2</sub> O <sub>3</sub>	%	16 – 20

**PACKAGING AND STORAGE:**

Shipped in either 3000 lbs. super sacks, 1000 lb. drums, 50 lb. bags, or 25 lb. bags. Other packaging options may also be available. Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 13.2

---

Phone: 1-800-609-5711  
[www.fedmet.com](http://www.fedmet.com)