

## **FLOSAN<sup>®</sup> Z30**

---

**DESCRIPTION:** Flosan<sup>®</sup> Z30 is a mixture of carefully selected and processed refractory materials with a high sintering point. The product is used as nozzle fill in sliding gate ladle systems and can also be used in E.B.T. furnace tapholes. Made with high purity zircon.

### **CHEMICAL ANALYSIS:**

		FLOSAN <sup>®</sup> Z30
Cr <sub>2</sub> O <sub>3</sub>	%	26 – 30
MgO	%	5 – 8
Al <sub>2</sub> O <sub>3</sub>	%	8 – 12
SiO <sub>2</sub>	%	14 – 18
C	%	Yes
Fe <sub>2</sub> O <sub>3</sub>	%	12 – 16
Zircon	%	28 – 33

### **PACKAGING AND STORAGE:**

Shipped in either 3000 lbs. super sacks, 1000 lb. drums, 50 lb. bags, or 25 lb. bags. Other packaging options may also be available. Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 13.2