

Fedcast 50 LI

DESCRIPTION: A general purpose low iron conventional castable refractory containing burn out fibers.

CHEMICAL ANALYSIS:

Approximate %

Alumina	Al ₂ O ₃	48-50
Silica	SiO ₂	40-42
Titania	TiO ₂	2-3
Ferric Oxide	Fe ₂ O ₃	< 1
Lime	CaO	6-7
Alkalis	Na ₂ O+K ₂ O	< 1
Other		< 2

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density (C865):

25°C (75°F)	2.1-2.3 g/cc (130-144 lb/ft ³)
110°C (230°F)	2.1-2.2 g/cc (130-137 lb/ft ³)
816°C (1500°F)	2.0-2.1 g/cc (125-130 lb/ft ³)
1370°C (2500°F)	1.9-2.0 g/cc (119-125 lb/ft ³)

Linear Change (C865):

110°C (230°F)	-0.2 to +0.0%
816°C (1500°F)	-0.4 to -0.0%
1370°C (2500°F)	+1.6 to +2.5%

Cold Crushing Strength (C133):

25°C (75°F)	21-25 MPa (3500-4500 psi)
110°C (230°F)	37-44 MPa (5500-6500 psi)
816°C (1500°F)	20-27 MPa (3000-4000 psi)
1370°C (2500°F)	31-41 MPa (4500-6000 psi)



INFORMATION BULLETIN

OTHER PROPERTIES:

Water Required: 10-14%

Maximum Hot Face Temperature: 1595°C (2900°F)

Maximum Grain Size: 4.7 mm (4 Mesh)

Dry Material Required for Use: 2000-2100 kg/m³ (125-130 lb/ft³)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 15.3