

### JEFRIT

---

**DESCRIPTION:** Electric furnace ramming mix, dry, manufactured from dead burned magnesia, with high lime content, reduced iron content, and high density.

**USES INCLUDE:** Hot repair of banks and bottoms of electric arc furnaces

48                      41

**CHEMICAL ANALYSIS: (Approximate % by weight)**

MgO	82	75
SiO <sub>2</sub>	0.8	1.5
Fe <sub>2</sub> O <sub>3</sub>	7	7.5
CaO	11	15
Al <sub>2</sub> O <sub>3</sub>	0.6	0.5

**TYPICAL AS RECEIVED PROPERTIES:**

Grain sizing, mm	0-8	0-8
------------------	-----	-----

**PACKAGE AND STORAGE:**

Shipped in 500, 1500 kg, 2000 kg bags.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.