

MGO Briquette 65

DESCRIPTION: MGO briquette slag conditioner

USES INCLUDE: High quality slagging additive is used in steel aggregates for increasing MGO content in a slag

CHEMICAL ANALYSIS: (Approximate % by weight)

MgO	65-67%
SiO ₂	8-11%
CaO	5%
Fe ₂ O ₃	below reportable levels
LOI - lost of ignition	20-30%

TYPICAL AS RECEIVED PROPERTIES:

Grain sizing, mm 20-40 mm, 3% max less than 20mm

PACKAGE AND STORAGE:

Shipped in 1000kg bags
Store pallets in a dry and protected area.

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 20.04