

Paragon PB

DESCRIPTION: Carbon-bonded dolomite brick

USES INCLUDE: Ladle working linings

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

Approximate % - calcined basis

Mgo	40%
CaO	60%
SiO ₂	0.5%
Fe ₂ O ₃	0.6%
Residual carbon	2.2%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity %	4
Bulk Density g/cm ³	2.93
Cold Crushing Strength n/mm ²	40

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 15.4

Phone: 1-800-609-5711

www.fedmet.com