

PARAGON PB6

DESCRIPTION: Carbon-bonded dolomite brick

USES INCLUDE: Ladle working linings

CHEMICAL ANALYSIS:

MgO	42 % by weight (approx.)
CaO	55
SiO ₂	0.3
Fe ₂ O ₃	0.6
Residual Carbon	6

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density, Original:	2.88 g/cm ³
Crushing Strength:	30 N/mm ²
Apparent Porosity:	4 %

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 15.4

Phone: 1-800-609-5711

www.fedmet.com