

## **PARAGON RD6**

---

**DESCRIPTION:** Carbon-bonded dolomite brick

**USES INCLUDE:** Ladle working linings

### **CHEMICAL ANALYSIS:**

MgO	42 % by weight (approx.)
CaO	55
SiO <sub>2</sub>	0.5
Fe <sub>2</sub> O <sub>3</sub>	0.6
Residual Carbon	6

### **TYPICAL AS RECEIVED PROPERTIES:**

Bulk Density, Original:	2.87 g/cm <sup>3</sup>
Crushing Strength:	85 N/mm <sup>2</sup>
Apparent Porosity:	4 %

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 15.4