

ATLAS 96TIZ: Burned Magnesite Brick w/ Zirconia

DESCRIPTION: Atlas 96TIZ

USES INCLUDE: BOF Q-BOP tuyere pad.

CHEMICAL ANALYSIS:

Approximate % - calcined basis

MgO	94 %
CaO	1.4%
Silica	1.6%
Fe ₂ O ₃	1.1%
Al ₂ O ₃	0.7%
ZrO ₂	2.0%

TYPICAL AS RECEIVED PROPERTIES:

Bulk Density g/cm ³ (pcf)	2.96 (184)
Cold Crushing Strength Mpa (psi)	100 (14500)
Apparent Porosity %	< 18 (before impregnation)
Modulus of rupture Mpa (psi)	
@22°C	15 (2175)
@1482°C	3 (435)
Refractoriness under load, °C (°F)	1610 (2930)

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.

Version 12.12

Phone: 1-800-609-5711

www.fedmet.com