

DURACHROME® FG50

DESCRIPTION: Semi-rebonded magnesia-chrome brick. Fortified with fused magnesia-chrome grain for improved density and corrosion resistance.

USES INCLUDE: Electric furnace roofs and sidewalls
AODs
Degassers
Copper Converters
Lead Smelters
Nickel Converters
Ladle Working and Tank Linings

CHEMICAL ANALYSIS: (TYPICAL CHEMICAL ANALYSIS)

Approximate-

Magnesia	MgO	58%
Chromic Oxide	Cr ₂ O ₃	20%
Silica	SiO ₂	0.5%
Alumina	Al ₂ O ₃	7%
Iron Oxide	Fe ₂ O ₃	13%
Lime	CaO	0.5%

TYPICAL AS RECEIVED PROPERTIES:

Apparent Porosity %	15
Bulk Density pcf (g/cm ³)	200(3.20)
CCS, psi(Mpa)	8050(55)
HMOR, 2700F psi (Mpa)	435(2.5)
RUL, °F(°C)	>3092(1700)
Thermal conductivity, BTU/sf/hr ² (W/MK)	
400°F(200°C)	25
800°F(426°C)	23
1200°F(648°C)	22

The values reported above are average values derived from production data encompassing many different sizes and shapes. Actual data will vary to a small degree naturally, and as a function of size and shape. This form is not intended to be used for purposes of specification, it is informational only.